

In re application of: LU, Fumin
Serial No. 09/778,454
Page 5

IN THE SPECIFICATION

Please amend the specification by adding the following new paragraph on page 1, line 19.

A2 The term R.V. shall mean relative viscosity and is a ratio. The term PA6 refers to nylon 6. The unit for melt flow rate is given in grams/10 minutes at 230 degrees Centigrade. The inherent viscosity of the polyester for the present invention is determined in a 0.5 wt. % (percentage) solution in a 60/40 phenol/tetrachloroethane solvent mixture. The determined inherent viscosity is then converted to intrinsic viscosity (I.V.) using an established formula.